

AD-A266 920



20

ARMY RESEARCH LABORATORY



The Effect of Plasma Treatment on Interfacial Bond Characteristics of Kevlar/Epoxy Laminates as Measured by T-Peel Tests

Rachel A. Machaud and Joey L. Mead

ARL-TR-141

May 1993

DTIC
ELECTE
JUL 15 1993
S A D

93-16005

Approved for public release; distribution unlimited.

93 7 1 078

The findings in this report are not to be construed as an official Department of the Army position unless so designated by other authorized documents.

Citation of manufacturer's or trade names does not constitute an official endorsement or approval of the use thereof.

Destroy this report when it is no longer needed. Do not return it to the originator.

REPORT DOCUMENTATION PAGE

Form Approved
OMB No. 0704-0188

Public reporting burden for this collection of information is estimated to average 1 hour per response, including the time for reviewing instructions, searching existing data sources, gathering and maintaining the data needed, and completing and reviewing the collection of information. Send comments regarding this burden estimate or any other aspect of this collection of information, including suggestions for reducing this burden, to Washington Headquarters Services, Directorate for Information Operations and Reports, 1215 Jefferson Davis Highway, Suite 1204, Arlington, VA 22202-4302, and to the Office of Management and Budget, Paperwork Reduction Project (0704-0188), Washington, DC 20503

1. AGENCY USE ONLY (Leave blank)		2. REPORT DATE May 1993		3. REPORT TYPE AND DATES COVERED Final Report	
4. TITLE AND SUBTITLE The Effect of Plasma Treatment on Interfacial Bond Characteristics of Kevlar/Epoxy Laminates as Measured by T-Peel Tests				5. FUNDING NUMBERS	
6. AUTHOR(S) Rachel A. Michaud and Joey L. Mead					
7. PERFORMING ORGANIZATION NAME(S) AND ADDRESS(ES) U.S. Army Research Laboratory Watertown, MA 02172-0001 ATTN: AMSRL-MA-PA				8. PERFORMING ORGANIZATION REPORT NUMBER ARL-TR-141	
9. SPONSORING/MONITORING AGENCY NAME(S) AND ADDRESS(ES) U.S. Army Research Laboratory 2800 Powder Mill Road Adelphi, MD 20783-1145				10. SPONSORING/MONITORING AGENCY REPORT NUMBER	
11. SUPPLEMENTARY NOTES					
12a. DISTRIBUTION/AVAILABILITY STATEMENT Approved for public release; distribution unlimited.				12b. DISTRIBUTION CODE	
13. ABSTRACT (Maximum 200 words) Composite materials are used in a wide variety of applications where their anisotropic properties allow the material to be tailored for each application. Unfortunately, aramid fiber composites may have limited applications due to poor transverse properties. These poor transverse properties are the result of weak interfacial bonding. Improvement of the interfacial bond strength has been an area of active research. Plasma treatment is one method that can be used to modify the surface of a fiber in an effort to improve the fiber-matrix adhesion. In this study, Kevlar/epoxy laminates were peel-tested (T-peel) to study the effect of plasma treatment on the interfacial properties. The T-peel results indicate that ammonia plasma treatment improves the interfacial bond strength of Kevlar/epoxy composites, increasing the T-peel strengths by approximately 30%.					
14. SUBJECT TERMS Composite materials, Epoxy composites, Kevlar fibers, Adhesion, Plasma treatment, T-peel				15. NUMBER OF PAGES 12	
				16. PRICE CODE	
17. SECURITY CLASSIFICATION OF REPORT Unclassified	18. SECURITY CLASSIFICATION OF THIS PAGE Unclassified	19. SECURITY CLASSIFICATION OF ABSTRACT Unclassified	20. LIMITATION OF ABSTRACT UL		

Contents

	Page
Introduction	1
Materials	1
Experimental	2
Results and Discussion	
T-peel Tests	2
Microscopy	6
Summary	8

Figures

1. T-peel test geometry	2
2. T-peel curve for fabric specimen group	3
3. T-peel curve for unidirectional fiber group	3
4. T-peel strength data	5
5. Failure surfaces of fabric specimens	6
6. Failure surfaces of unidirectional materials	7

Tables

1. T-peel test results	4
----------------------------------	---

DTIC QUALITY INSPECTED 8

Accession For	
NTIS CRA&I	<input checked="" type="checkbox"/>
DTIC TAB	<input type="checkbox"/>
U. announced	<input type="checkbox"/>
Justification	
By	
Distribution /	
Availability Codes	
Dist	Avail and/or Special
A-1	

Introduction

Polymer composite materials possess high specific strength and stiffness properties. These advantageous features, combined with competitive cost compared with metals, are driving composites into widespread application. They are commonly used in aerospace, military, sporting goods, and transportation to name a few major markets.

The interfacial bond that exists between the fiber and matrix of a composite is an important component of composite materials as it facilitates load transfer between fibers. Composites having weak interfacial bonds have low interlaminar and intralaminar shear strengths. Allred, et al. [1] have shown that moisture can weaken the fiber-matrix interface in aramid/epoxy composites, leading to poor transverse properties in wet environments. Improvement in fiber-matrix bonding should produce composites with greater resistance to property degradation by moisture.

Aramid fiber composites are especially hindered by poor interfacial bonds, and improvement of the interfacial bond strength has been an area of active research. Creation of covalent bonding sites on the fiber surface is expected to increase the interfacial strength between the fiber and resin. Stoller, et al. [2] treated Kevlar fibers to modify their surface chemistry by an ammonia plasma process. This process introduces reactive amine groups to the surface of the fiber that are potential covalent bonding sites between the fiber and resin through participation of the amine group in the epoxy curing reaction.

To evaluate qualitatively the interfacial bond strength of fibrous composite Kevlar/epoxy laminates a peel test (T-peel) was performed using ASTM D1876, "Standard Test Method for Peel Resistance of Adhesives (T-peel Test)" as a reference. In this study, the laminates were T-peel tested in order to study the effect of plasma treatment on the interfacial properties. The T-peel results indicate that ammonia plasma treatment improves the interfacial bond strength of Kevlar/epoxy composites, increasing the T-peel strengths by approximately 30%.

Materials

The Kevlar/epoxy specimens studied were two-ply laminates obtained from PDA Engineering (now TPL, Incorporated) under a Phase II Small Business Innovative Research (SBIR) contract. Two different types of specimens were evaluated. One type of laminate was prepared from plain weave fabric and the other was prepared from unidirectional tape. In the unidirectional material, the fiber was aligned parallel to the long axis of the specimen. Ten control and ten plasma treated specimens were studied from each group.

The fabric specimens were prepared using Kevlar 49 (style 281) treated in an ammonia plasma batch process. Unidirectional Kevlar/epoxy prepreg was prepared by treating 7100 denier roving in a continuous ammonia plasma treatment-resin

1. ALLRED, R. E., and ROYLANCE, D. K. *Transverse Moisture Sensitivity of Aramid/Epoxy Composites*. Journal of Materials Science, v. 18, 1983, p. 652-656.
2. ALLRED, R. E., HARRAH, L. A., SALAS, R. M., and GORDON, B. W. *Plasma Treatment Processes for Improved Interfacial Adhesion in Kevlar/Epoxy Composites*. SBIR Phase II Final Report, MTL TR 90-60, November 1990.

impregnation facility developed under the SBIR Phase II program [2]. The epoxy resin used was Epon 826, a diglycidyl ether of bis-phenol A epoxy, cured with Epon curing agent Z (both products of Shell Chemical Company). For a detailed description of the processing and preparation of these specimens refer to Reference 2.

Experimental

All specimens in the study were rectangular with a 1 in. width. The fabric specimens were 6 in. long, and the unidirectional specimens were 12 in. long. One inch of the laminate length was not bonded to allow the specimen to be clamped into the grips of the testing machine, as shown in Figure 1.



Figure 1. T-peel test geometry.

The laminates were T-peel tested in a floor model Instron screw-type test machine to determine interlaminar shear strength. ASTM D1876 was used as a reference for the procedure, but the crosshead speed was changed to 2 in./minute. The unbonded end of the specimen was bent at a 90° angle to the bonded end of the specimen and clamped into the test grips. The test load data was collected with an IBM personal computer using a Keithley data acquisition system. The Instron chart recorder was used as a backup for the computer. The raw data was reduced separately in a later analysis.

During testing the computer sampled voltage signals from the Instron at a rate of 10 points per second. The raw data was later converted to load values and averaged using another program. All valid data points from the initial peak to the end of the test were used to calculate the average load value. For the fabric specimens, the end of the test was the point when the specimen was completely peeled apart. For the unidirectional specimens, the test was ended after the first 9 in. were peeled. The T-peel strength was calculated by dividing the average load by the specimen width. After testing, the specimen failure surfaces were studied under an optical microscope to compare differences between the control and treated specimens.

Results and Discussions

T-Peel Tests

The T-peel test is generally used to study the effectiveness of an adhesive bond to increase the peel resistance between two adherends. During a T-peel test the force builds up until fracture initiates and the energy is released. The force then builds up again and the fracture cycle is repeated. This test geometry favors failure between the plies; therefore, the load needed to initiate the fracture cycle should be

related to interlaminar bond strength [3]. Figure 2 compares the typical continuous load per unit width versus crosshead displacement curve obtained for representative fabric control and treated specimens. Figure 3 shows the same curve generated for typical unidirectional specimens.




Figure 2. T-peel curve for fabric specimen group.




Figure 3. T-peel curve for unidirectional fiber group.

3. STOLLER, H. M., DELOLLIS, N. J., and RODACY, C. *Plasma Treatment Optimization of Polyaramid Filaments to Improve Kevlar/Epoxy Composites*. SBIR Phase I Final Report, PIDA Engineering, May 1986.

The fabric specimens show a jagged curve indicating crack propagation-crack arrest cycles, while the unidirectional specimens exhibit a smoother fracture curve more representative of continuous crack propagation. The T-peel test results for each specimen are listed in Table 1.

Table 1. T-peel test results

T-peel tests			
Fabric control		Fabric treated	
Specimen (number)	Avg load (lb/in.)	Specimen (number)	Avg load (lb/in.)
1	2.07	11	2.35
2	2.05	12	2.16
3	1.85	13	2.62
4	2.29	14	2.53
5	2.45	15	2.46
6	2.06	16	2.38
7	2.06	17	3.01
8	2.01	18	3.12
9	1.51	19	3.05
10	1.68		
	Avg		Avg
	2.00		2.63
	Std		Std
	0.26		0.33

Unidirectional control		Unidirectional treated	
Specimen (number)	Avg load (lb/in.)	Specimen (number)	Avg load (lb/in.)
1	4.45	11	5.33
2	4.55	12	6.61
3	4.92	13	7.02
4	4.35	14	6.53
5	5.27	15	6.22
6	6.37	16	5.57
7	5.11	17	5.72
8	4.29	18	7.14
9	4.31	19	6.64
10	5.39		
	Avg		Avg
	4.90		6.31
	Std		Std
	0.63		0.61

Figure 4 compares all the specimens with one standard deviation range. These data show that higher values of T-peel strength are obtained for the plasma treated specimens. The fabric specimens show an increase of 32% in the T-peel strength with ammonia plasma treatment. The unidirectional specimens show an increase of

29% in T-peel strength with continuous plasma treatment. This indicates the plasma treatment is effective in promoting improved adhesion between the fiber and matrix. Modification of the Kevlar surface with an ammonia plasma offers a method for improving the mechanical properties of Kevlar/epoxy composites as evidenced by the higher peel strengths obtained for plasma treated specimens. The values obtained for the fabric controls in this study are in line with those obtained in the Phase II SBIR report (the untreated specimens had values of 1.9 lb/in. in the Phase II study) [2], but the values found in this study for the treated fabric specimens are lower (treated specimens had values of about 4 lb/in. in the Phase II study) [2].




Figure 4. T-peel strength data.

Microscopy

Figures 5 and 6 compare the failure surfaces of the fabric and unidirectional specimens, respectively. There are no discernible differences in the failure surfaces of the treated and untreated specimens. However, further microscopy study, particularly scanning electron microscopy, should be performed to further explore the effects of plasma treatment.



Figure 5. Failure surfaces of fabric specimens.




Figure 6. Failure surfaces of unidirectional materials.

Summary

The results of the T-peel tests indicate that ammonia plasma treatment is effective in improving the fiber-matrix adhesion and the mechanical properties of Kevlar/epoxy composites. The treated fabrics show an increase of 32% in the T-peel strength when compared to the control. The treated unidirectional material shows an increase of 29% when compared to the control data set. These data are in agreement with the results obtained by Allred, et al. [2] that report ammonia plasma treatment increases the interfacial bond strength leading to improved mechanical properties for the treated materials.

DISTRIBUTION LIST

No. of Copies	To
1	Office of the Under Secretary of Defense for Research and Engineering, The Pentagon, Washington, DC 20301
	Director, U.S. Army Research Laboratory, 2800 Powder Mill Road, Adelphi, MD 20783-1197
1	ATTN: AMSRL-OP-CI-AD, Technical Publishing Branch
1	AMSRL-OP-CI-AD, Records Management Administrator
	Commander, Defense Technical Information Center, Cameron Station, Building 5, 5010 Duke Street, Alexandria, VA 22304-6145
2	ATTN: DTIC-FDAC
	Commander, Army Research Office, P.O. Box 12211, Research Triangle Park, NC 27709-2211
1	ATTN: Information Processing Office
	Commander, U.S. Army Materiel Command, 5001 Eisenhower Avenue, Alexandria, VA 22333
1	ATTN: AMCSCI
	Commander, U.S. Army Materiel Systems Analysis Activity, Aberdeen Proving Ground, MD 21005
1	ATTN: AMXSY-MP, H. Cohen
	Commander, U.S. Army Missile Command, Redstone Arsenal, AL 35809
1	ATTN: AMSMI-RD-CS-R/Doc
	Commander, U.S. Army Armament, Munitions and Chemical Command, Dover, NJ 07801
2	ATTN: Technical Library
	Commander, U.S. Army Natick Research, Development and Engineering Center, Natick, MA 01760-5010
1	ATTN: Technical Library
1	Janet E. Ward
1	Heidi Gibson
	Commander, U.S. Army Satellite Communications Agency, Fort Monmouth, NJ 07703
1	ATTN: Technical Document Center
	Commander, U.S. Army Tank-Automotive Command, Warren, MI 48397-5000
1	ATTN: AMSTA-ZSK
1	AMSTA-TSL, Technical Library
	Commander, White Sands Missile Range, NM 88002
1	ATTN: STEWS-WS-VT
	President, Airborne, Electronics and Special Warfare Board, Fort Bragg, NC 28307
1	ATTN: Library
	Director, U.S. Army Research Laboratory, Aberdeen Proving Ground, MD 21005
1	ATTN: AMSRL-WT
	Commander, Dugway Proving Ground, UT 84022
1	ATTN: Technical Library, Technical Information Division
	Commander, U.S. Army Research Laboratory, 2800 Powder Mill Road, Adelphi, MD 20783
1	ATTN: AMSRL-SS
	Director, Benet Weapons Laboratory, LCWSL, USA AMCCOM, Watervliet, NY 12189
1	ATTN: AMSMC-LCB-TL
1	AMSMC-LCB-R
1	AMSMC-LCB-RM
1	AMSMC-LCB-RP
	Commander, U.S. Army Foreign Science and Technology Center, 220 7th Street, N.E., Charlottesville, VA 22901-5396
3	ATTN: AIFRTC, Applied Technologies Branch, Gerald Schlesinger
	Commander, U.S. Army Aeromedical Research Unit, P.O. Box 577, Fort Rucker, AL 36360
1	ATTN: Technical Library

No. of Copies	To
1	U.S. Army Aviation Training Library, Fort Rucker, AL 36360 ATTN: Building 5906-5907
2	Naval Research Laboratory, Washington, DC 20375 ATTN: Dr. G. R. Yoder - Code 6384
1	Chief of Naval Research, Arlington, VA 22217 ATTN: Code 471
1	Commander, U.S. Air Force Wright Research & Development Center, Wright-Patterson Air Force Base, OH 45433-6523 ATTN: WRDC/MLLP, M. Forney, Jr.
1	WRDC/MLBC, Mr. Stanley Schulman
1	NASA - Marshall Space Flight Center, MSFC, AL 35812 ATTN: Mr. Paul Schuler/EH01
1	General Dynamics, Convair Aerospace Division P.O. Box 748, Forth Worth, TX 76101 ATTN: Mfg. Engineering Technical Library
1	NASA - Langley Research Center, Hampton, VA 23665-5225
1	U.S. Army Vehicle Propulsion Directorate, NASA Lewis Research Center, 2100 Brookpark Road, Cleveland, OH 44135-3191 ATTN: AMSRL-VP
1	NASA - Lewis Research Center, 2100 Brookpark Road, Cleveland, OH 44135-3191
1	Director, Defense Intelligence Agency, Washington, DC 20340-6053 ATTN: ODT-5A (Mr. Frank Jaeger)
1	Boeing Aerospace Company, P.O. Box 3999, Seattle, WA 98124-2499 ATTN: Donald E. Wright, MS 6K-43
1	Adherent Technologies, 9621 Camino del Sol, NE, Albuquerque, NM 87111 ATTN: Ronald E. Allred
1	TPL, Inc., 3754 Hawkins, NE, Albuquerque, NM 87109 ATTN: H.M. Stoller
2	Director, U.S. Army Research Laboratory, Watertown, MA 02172-0001 ATTN: AMSRL-OP-CI-D, Technical Library
10	Authors